







Line: Complementary products Category: Hardeners	Type: Liquid hardeners Code: 3041.02
Name or commercial logo: <b>C/RL</b>	
<b>Nature:</b> mixture of methyletylketone peroxide in 1-isopropyl-2,2-dimethyltrimethylene diisobutyrate <b>Use:</b> crosslinker for spray fillers with a base of unsaturated polyester resins. <b>Peculiarities:</b> <ul style="list-style-type: none"> <li>• product formulated for the total polymerization of the impregnation resin R/L;</li> <li>• compound featured by a relatively short gel-time and a gradual gelation;</li> <li>• it allows the hardening of great thickness without tensionatures or fractures.</li> </ul>	
<b>Physical features:</b>	
Aspect: Liquid Color: Colorless Odour: Similar to ketones	Specific weight: 1,013 kg/l Viscosity: 13,1 mPa*s Active oxygen content: 9,8 - 9,9%
<b>Technical features:</b>	
Self-accelerating decomposing temperature (SADT):	> 65 °C
<b>Applicative data:</b>	
	From 5 °C to 20 °C - Resin                      100 parts + Hardener 3 v.p. From 21 °C to 25 °C - "                              100 parts                              "                              2 v.p. Above 25 °C    "    100 parts                              "                              1 v.p.
	Close tightly the container after use.
	<u>HEATING MAY CAUSE A FIRE</u> , (See Security Data Sheet, p. 5)
	Store the product away from direct sunlight in original tightly closed sealed packaging, away from acids, reducing agents and promoters of polymerization.
	The storage room should be dry and the temperature between 10 °C and 30 °C. The product, when stored under the above conditions, preserves itself for 3 months from the date of shipment.
<b>Warnings and Precautions:</b>	
	<ul style="list-style-type: none"> <li>- Read carefully the Safety Data Sheet before use</li> <li>- Product specifically for PROFESSIONAL USE</li> </ul>

**Consumer information:**

The information here contained are based on our knowledge at the moment. We reserve the right to make changes in the characteristic data of the product in relation with technological progress or productive developments. Due to factors beyond our control in the applicative phase of the product, the information here contained are not a form of guarantee for specific qualities of the product itself, nor its suitability for a specific application. If a responsibility is determined, this will be limited to the value of the provided products used by the consumer. We guarantee however the constancy in the quality of our products. Our responsibility concerns only the area of the General Sales Conditions. This Technical Data Sheet supersedes all the previous.

